



Sorte	Korngröße	Binder	Dichte	Härte	Biegebruchfestigkeit
Grade	Grain-Size	Binder	Density ± 0,10	Hardness ± 50	TRS ± 100
		%	g/cm ³	HV30	Mpa
K10	fine	5,5	14,90	1700	2400
K20	fine	6,0	14,85	1630	2600
K30	fine	9,0	14,65	1470	2800
K40F	submicron	10,0	14,45	1630	3700
K30 Nickel	fine	10% Ni 0,5% Cr ₃ C ₂	14,45	1350	2200
GT20	medium	12,0	14,35	1320	3100
GT30	medium	15,0	13,95	1180	3200

Alle Sorten werden in HIP-Qualität geliefert.
All Grades are supplied in HIP-Quality.

Mit diesen Angaben werden HM-Sorten spezifiziert, nicht Eigenschaften zugesichert.
These informations specify TC-Grades, not the properties of Tungsten-Carbides.

